

WILSONART ADHESIVES CERTIFIED PRODUCT DATA SHEET



This chart lists the volatile organic compound (VOC) and volatile hazardous air pollutant (VHAP) content of Wilsonart Adhesives.

As provided for in 40CFR805.a for coatings which do not release VOC or VHAP by-products during the cure, the VHAP information given below is based on formulation data.

The information contained in this document is provided to assist the user of these products in complying with the appropriate federal, state and local laws and regulations. Although Wilsonart International, Inc. believes the data contained herein to be accurate and to have been derived from reliable sources, the provision of this information is not intended to constitute a warranty or a representation of performance by Wilsonart International, Inc.

Certified by Wilsonart International, Inc., Dec. 12, 2011.

Adhesive Type	VHAP Content ¹ (lbs.VHAP/lbs. Solids)	VHAP Content ¹ (lbs. VHAP/gal)	VOC Content ² (g/L) / (lbs./gal)	VOC per Liter of Material ³ (g/L) / (lbs./gal)	Density ⁴ (lbs./gal)	Solids Content ⁴ (% by weight)
WA 500	0.83	1.09	601 / 5.01	448 / 3.74	6.73	19.50
WA 600	1.25	1.75	671 / 5.60	669 / 5.58	7.00	20.00
WA 800/801	0.66	0.79	596 / 4.98	418 / 3.49	6.66	18.00
WA 810/811	0.08	0.11	534 / 4.46	283 / 2.36	6.87	20.50
WA 844/845	0.39	0.46	575 / 4.80	372 / 3.10	6.63	18.00
WA 860/861	0.70	0.79	603 / 5.03	419 / 3.50	6.63	17.00
WA 950/951	0.75	0.84	606 / 5.06	435 / 3.63	6.62	17.00
WA 981	0.70	0.79	602 / 5.02	417 / 3.48	6.64	17.00
WA 1700/1701	0.00	0.00	8 / 0.07*	3 / 0.02*	7.77	35.00
WA 1730/1731	0.03	0.08	78 / 0.65	31 / 0.26	8.46	35.00

1: VHAP content indicates VHAP which are present in amounts greater than or equal to 1.0 percent by weight (or, for OSHA defined carcinogens, greater than 0.1 percent by weight). VHAP content based on lowest acceptable solids to solvent ratio, thus actual VHAP content may be slightly less.

2: VOC content calculated per EPA Method 24 and SCAQMD Rule 443.1(f) which excludes water and exempt solvents. VOC content based on lowest acceptable solids to solvent ratio, thus actual VOC content may be slightly less.

3: Calculated per SCAQMD Rule 443.1 (g). VOC per liter of material based on lowest acceptable solids to solvent ratio, thus actual VOC may be slightly less.

4: Density and Solids content based on formulation data and on lowest acceptable solids to solvent ratio, thus actual solids content may be as much as 2% greater than that shown, and is formulated to be 0.5% to 1.0% greater than the solids content shown.

*TBAC IS RECOGNIZED IN 40 C.F.R. 51.100(s) AND BY THE EPA AS A VOC EXEMPT COMPOUND. ALASKA, CALIFORNIA, KANSAS, WYOMING AND WASHINGTON D.C. HAVE NOT FORMALLY RECOGNIZED THIS EXEMPTION. CONTACT YOUR LOCAL REGULATORY AGENCY TO PROVIDE CLARIFICATION ON THE EXEMPTION STATUS.

Wilsonart LLC
10601 NW HK Dodgen Loop
Temple, Texas 76504
1.800.433.3222
Email: adhesives@wilsonart.com
www.wilsonartadhesives.com

©2013 Wilsonart LLC
Revised 6/2014